



## TRUST FINE TEXTURED ROLL

**High quality pigmented continuous wall coating in smooth rolled texture.**

- **USES**

On all types of interior and exterior surfaces such as rendered mortars, Gypsum plasters etc. Whenever one wants to obtain a good aesthetical appearance in a specific texture, as well as a resistance to abrasion or shocks.

- **TECHNICAL CHARACTERISTICS**

**Composition:**

Based on acrylic polymers in aqueous emulsion, quartz powders and sands calibrated & selected marble grains, organic and inorganic pigments with outstanding characteristics, of resistance to light and alkali, additives which give the product excellent filming characteristics, workability and resistance to bacterial attacks.

**Average specific weight:**

About 1.65 kg/dm<sup>3</sup>

**Viscosity:**

About 30,000 cPs

**Solid content:**

About 73% in weight

**Minimum film**

**Forming temperature:**

+ 5°C

**Drying time:**

About 2 to 6 hours. The drying time required is variable in relation to the temperature and humidity existing at the moment of application.

**Appearance of the film:**

Textured Mat coating. Satin or gloss finish also attainable by applying a finishing coat of Trust Superglaze.

- **ADVISED CONSUMPTION**

About 1.0 - 1.2 KG/M<sup>2</sup>. The actual consumption required will be dependent on the conditions of the substrates to be coated and on the appearance to be attained in the specific texture.

- **COLORS AVAILABLE**

White plus the colors presented in our catalogue.

- **PACKINGS**

Drums of 25 kg.

## INSTRUCTIONS FOR USE

### • Surface treatment of the substrate

**On thin rendered mortars:** a) An undercoat of Trust LE thinned 1: 5 with water

**On Gypsum plasters or other very smooth surfaces:** a) An undercoat of Trust Enamel Undercoat

**On metals** a) An undercoat of anti-rust primer metal.

**On old plasters which are chalky, absorbent and degraded:**

- a) Carefully remove all parts, which are not securely anchored to the background and restore the surface where necessary.
- b) An undercoat of primer of Trust Enamel Undercoat

N.B On the substrate treated as above give a coat of TRUST Roll thinned from 50 to 100% in water in the same color as that of the final coating. On thin rendered mortars and gypsum plasters, TRUST Roll fine thinned with 100% of water may be used instead of the primers.

In every case however, before the application, the background should be dry, clean of any traces of grease or form-oils, where possible slightly rough and however highly consolidated in order to support the load of the coating to be applied.

### • Method of application

- a) If desired, thin the product with water up to a maximum of 10%, but always in a constant measure for the whole lot to be applied.
- b) Apply the TRUST Roll with a normal paintbrush a color Roll.
- c) Roll over the coating with a sponge roller in order to obtain the texture, but remembering to make the final rolling all in the same direction.

### • STORAGE

The product must be stored in well-closed drums, at temperatures not inferior to 0°C, protected from direct sunshine and strong heat.

### • WARNING AND SUGGESTIONS

Use only fresh, clean water for thinning and mix well before use. The ambient temperature for application is recommended to be between + 5°C and + 40°C.

The technical data and methods reported in this technical data sheet are subject to variations at any time according to the latest development in the production technology. The technical service of Trust is at the user disposal for the supply of integrative information to the herein reported.