



TRUST SEMI GLOSS ENAMEL

High quality washable Semi Gloss Enamel for interiors and exteriors.
Series 800

• USES

For painting of all types of internal and external walls where. In addition the normal performance of high quality all alkyd Semi-gloss paint one requires an outstanding resistance to wet abrasion. In addition it is ideal for plaster, wallboard, wood or metal in kitchens, bathrooms, laundry rooms, halls and all around the house, especially in high traffic areas where washability is essential.

• TECHNICAL CHARACTERISTICS

Composition:

Based on all alkyd Semi-gloss, and will not permit grease and hand smudges to adhere to its surface. Flows out to a smooth even film, free of brush marks and roller patterns and clings to sharp molding and trim edges. Titanium dioxide, carefully selected fillers and additives which give the product excellent filming characteristics, workability making the product highly resistant to light and alkali.

Average specific weight:

1. Pigment: 30.5%
Titanium dioxide: 30.7%
Silica: 2.6%
2. Vehicle: 58.51%
Alkyd resin: 60.5%
Volatile material: 20%

Minimum film

Forming temperature: + 5°C

Resistance to alkali: Very good

Washability: 20,000 Gardner cycles

Appearance of the film: Semi-gloss

Drying time: (temperature & humidity dependent).
@77°F, 50%rh, 4.0 mils wet.
Dust free 2-4 hours.
Re-coat in 12 hours.
Full cure 5 days.

• ADVISED CONSUMPTION

About 40 - 50M²/Gallon.

• **COLORS AVAILABLE** White, basic colors and any of the colors presented in our color guide.

• **PACKING** Drums of 20 Liter & USG

Instructions for use

• Surface treatment of the substrate

On new, thin rendered mortars: a) Brush and roller over the surface well.
b) An undercoat of the same Trust series 800 “Enamel Undercoat” thinned with 50% of white spirit.

On surfaces to be repainted: a) Brush and roller over the surface well
b) An undercoat of primer Enamel “series 700” based thinned 50% white spirit

On old plasters which are chalky, absorbent and degraded: a) carefully remove all parts which are not securely anchored to the background and restore the surface where necessary.

N.B. In every case however, before the application, the substrate should be dry, clean of any traces of grease or from-oils and any parts not perfectly anchored to the background.

• Method of application

After an adequate preparation of the substrate, according to the above indications, apply the product by the brush, or roller as follows:

- a) A first coat of Trust Semi-Gloss-Enamel thinned with about 15% of white spirit.
- b) A second coat of Trust Semi-Gloss Enamel thinned with about 20% of white spirit.

N.B. The product may also be applied by the spray even with airless type sprayer.

• Storage

The product must be stored in well closed container, at temperatures not inferior to 0°C, protected from direct sunshine and strong heat.

• Warnings and suggestions

Use only white spirit for thinning and mix well before use. The application should be carried out sheltered from direct sunshine, strong winds and rain. The ambient temperature for application is recommended to be between +5°C and +40°C. In addition it contains Aliphatic Hydrocarbons. Combustible, Keep away from heat open flame. Close container after each use. Protect from freezing. Use with adequate ventilation.

The technical data and methods reported in this technical data sheet are subject to variations at any time according to the latest development in the production technology. The technical service of Trust is at the user disposal for the supply of integrative information to the herein reported.